

EMI/EMC SHIELDED GASKET:

Special Features:


- ❖ High Shielding Effectiveness
- ❖ Minimum Galvanic Corrosion

Properties:

- ❖ Composition: Silicon with Nickel coated Graphite
- ❖ Product Name: Conductive Sheet.
- ❖ Nomenclature: SR-NCG-43.
- ❖ Color: Grey
- ❖ Shielding Effectiveness > 45dB measured as per ASTM-ES-7-83
- ❖ Hardness (Shore A): 75 ± 5 measure per ASTM Standard D 2240
- ❖ Density: 1.9 ± 0.2 gm/cc measure per ASTM Standard D 792
- ❖ Tensile Strength: > 1.5 Mpa measured per ASTM Standard D412
- ❖ Elongation at break: > 100% measured per ASTM Standard D412
- ❖ Temperature Range: -45°C to 120°C
- ❖ Volume Resistivity: <0.1 ($\Omega \cdot \text{cm}$) tested per testing standard MIL-DTL-83528C.
- ❖ Outgassing properties: Meets NASA outgassing property TML < 1 % and CVCM < 0.1 %.
- ❖ Size: Can be supplied given in desired size.

Other Products: Other customized molded/extruded products can be made.

GLOBAL PRESENCE



LASER CUTTING RF & Microwave
MARKING Medical Devices
WELDING Hi-Tech Software
 Diamond Processing
 Renewable Energy
 Cleaning
 Scribing / Dicing
 Automations

DEFENCE & AEROSPACE
MICRO MACHINING

SLTL'S STRENGTH

<p>Experience</p> <p>34+ Years</p>	<p>Mfg. Plants</p> <p>6 Laying Over</p> <p>54000 Sq. mtr.</p>	<p>10%</p> <p>Yearly R&D</p>	<p>Exports</p> <p>40+</p> <p>Countries</p>
<p>15000+</p> <p>Systems</p>	<p>ISO</p> <p>9001-2015</p>	<p>26+</p> <p>Patents</p>	<p>29+</p> <p>Awards</p>



CE An ISO 9001:2015 Certified Company

Sahajanand Laser Technology Ltd. (SLTL Group)

E-30, Electronic Estate, G.I.D.C., Sector - 26,
 Gandhinagar - 382 028, Gujarat, India.
 Tel : +91-79-6170-1616 | Fax : +91-79-2328-7470

+91-90-9907-1094 | microwave@SLTL.in



Scan to Visit
www.SLTLmicrowave.com